



JOANNE / J.F. FABRICS

PRODUCT INFORMATION

Nashville - J3741

---




# Nashville

*Yee-ha Cowboy!*

**Nashville** is a fun and flirty collection of casual yet sophisticated cotton blend plaids, stripes, and checks, combining an enduring faux suede, *Sensa* and a textured colorful chenille, *Maverick* to compliment the whole package. **Nashville's** theme has an upscale country flare and with a full color palette of 104 skus it is sure to fit any design project. All patterns run up the roll and are suitable for drapery, bedding, upholstery and decorative upholstery.



Let your imagination run wild.





	<p><b>PATTERN</b>  Number of Cols. 3  Content 100% Cotton  Country of Origin India  Width 54" - 137 cm  Vertical 0.625" (1.6 cm)  Horizontal 0.75" (1.9 cm)  Railroaded No  Weight (oz/ln yd) 10.2  Care Code S  Flammability N/A  Surface Abrasion 15,000 DR Wyzenbeek Cotton Duck  Tear Strength N/A  Seam Slippage N/A  Breaking Strength N/A  Colorfastness to Light N/A  Crocking N/A  Pilling N/A</p>	<p><b>HORSESHOE</b>  3  100% Cotton  India  54" - 137 cm  0.625" (1.6 cm)  0.75" (1.9 cm)  No  10.2  S  N/A  15,000 DR Wyzenbeek Cotton Duck  N/A  N/A  N/A  N/A  N/A</p>
	<p><b>PATTERN</b>  Number of Cols. 13  Content 80% Cotton, 14% Polyester, 6% Viscose  Country of Origin Turkey  Width 54" - 137 cm  Vertical 1.3" (3.3 cm)  Horizontal 1.2" (3 cm)  Railroaded No  Weight (oz/ln yd) 11.8  Care Code S  Flammability UFAC Class/e 1, Cal. 117  Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck  Tear Strength N/A  Seam Slippage Warp: 111.4 lbf, Filling: 39 lbf  Breaking Strength N/A  Colorfastness to Light Class/e 4.5 (40 hours)  Crocking Wet: Class/e 4.5, Dry: Class/e 4.5  Pilling Class/e 3</p>	<p><b>LODGE</b>  13  80% Cotton, 14% Polyester, 6% Viscose  Turkey  54" - 137 cm  1.3" (3.3 cm)  1.2" (3 cm)  No  11.8  S  UFAC Class/e 1, Cal. 117  30,000 DR Wyzenbeek Cotton Duck  N/A  Warp: 111.4 lbf, Filling: 39 lbf  N/A  Class/e 4.5 (40 hours)  Wet: Class/e 4.5, Dry: Class/e 4.5  Class/e 3</p>
	<p><b>PATTERN</b>  Number of Cols. 9  Content 100% Cotton  Country of Origin India  Width 54" - 137 cm  Vertical N/A  Horizontal 6.75" (17.1 cm)  Railroaded No  Weight (oz/ln yd) 9  Care Code S  Flammability UFAC Class/e 1, Cal. 117  Surface Abrasion 6,700 DR Wyzenbeek Cotton Duck  Tear Strength Warp: 10.9 lbf, Filling: 5 lbf  Seam Slippage Warp: 56.8 lbf, Filling: 39.7 lbf  Breaking Strength Warp: 96.2 lbf, Filling: 62.1 lbf  Colorfastness to Light N/A  Crocking Wet: Class/e 3.5, Dry: Class/e 4.5  Pilling Class/e 4</p>	<p><b>LONESTAR</b>  9  100% Cotton  India  54" - 137 cm  N/A  6.75" (17.1 cm)  No  9  S  UFAC Class/e 1, Cal. 117  6,700 DR Wyzenbeek Cotton Duck  Warp: 10.9 lbf, Filling: 5 lbf  Warp: 56.8 lbf, Filling: 39.7 lbf  Warp: 96.2 lbf, Filling: 62.1 lbf  N/A  Wet: Class/e 3.5, Dry: Class/e 4.5  Class/e 4</p>

	<p><b>PATTERN</b>  Number of Cols. 13  Content 46% Viscose, 36% Polyester, 18% Cotton  Country of Origin India  Width 54" - 137 cm  Vertical N/A  Horizontal N/A  Railroaded No  Weight (oz/ln yd) 16.2  Care Code S  Flammability UFAC Class/e 1, Cal. 117  Surface Abrasion 12,000 DR Wyzenbeek Cotton Duck  Tear Strength Warp: resists tear, Filling: 50.2 lbf  Seam Slippage Warp: 88.3 lbf, Filling: 70 lbf  Breaking Strength Warp: 350.98 lbf, Filling: 171.04 lbf  Colorfastness to Light N/A  Croaking Wet: Class/e 4, Dry: Class/e 4.5  Pilling Class/e 3</p>	<p><b>MAVERICK</b>  13  46% Viscose, 36% Polyester, 18% Cotton  India  54" - 137 cm  N/A  N/A  No  16.2  S  UFAC Class/e 1, Cal. 117  12,000 DR Wyzenbeek Cotton Duck  Warp: resists tear, Filling: 50.2 lbf  Warp: 88.3 lbf, Filling: 70 lbf  Warp: 350.98 lbf, Filling: 171.04 lbf  N/A  Wet: Class/e 4, Dry: Class/e 4.5  Class/e 3</p>
	<p><b>PATTERN</b>  Number of Cols. 3  Content 100% Cotton  Country of Origin India  Width 54" - 137 cm  Vertical 0.875" (2.2 cm)  Horizontal 0.875" (2.2 cm)  Railroaded No  Weight (oz/ln yd) 10.3  Care Code S  Flammability N/A  Surface Abrasion 15,000 DR Wyzenbeek Cotton Duck  Tear Strength N/A  Seam Slippage N/A  Breaking Strength N/A  Colorfastness to Light N/A  Croaking N/A  Pilling N/A</p>	<p><b>MISSION</b>  3  100% Cotton  India  54" - 137 cm  0.875" (2.2 cm)  0.875" (2.2 cm)  No  10.3  S  N/A  15,000 DR Wyzenbeek Cotton Duck  N/A  N/A  N/A  N/A  N/A  N/A</p>
	<p><b>PATTERN</b>  Number of Cols. 8  Content 100% Cotton  Country of Origin India  Width 54" - 137 cm  Vertical N/A  Horizontal 1.0625" (2.7 cm)  Railroaded No  Weight (oz/ln yd) 9  Care Code S  Flammability UFAC Class/e 1, Cal. 117  Surface Abrasion 6,700 DR Wyzenbeek Cotton Duck  Tear Strength Warp: 10.9 lbf, Filling: 5 lbf  Seam Slippage Warp: 56.8 lbf, Filling: 39.7 lbf  Breaking Strength Warp: 96.2 lbf, Filling: 62.1 lbf  Colorfastness to Light N/A  Croaking Wet: Class/e 3.5, Dry: Class/e 4.5  Pilling Class/e 4</p>	<p><b>OUTLAW</b>  8  100% Cotton  India  54" - 137 cm  N/A  1.0625" (2.7 cm)  No  9  S  UFAC Class/e 1, Cal. 117  6,700 DR Wyzenbeek Cotton Duck  Warp: 10.9 lbf, Filling: 5 lbf  Warp: 56.8 lbf, Filling: 39.7 lbf  Warp: 96.2 lbf, Filling: 62.1 lbf  N/A  Wet: Class/e 3.5, Dry: Class/e 4.5  Class/e 4</p>

	<p><b>PATTERN</b>  Number of Cols.  Content  Country of Origin  Width  Vertical  Horizontal  Railroaded  Weight (oz/ln yd)  Care Code  Flammability  Surface Abrasion  Tear Strength  Seam Slippage  Breaking Strength  Colorfastness to Light  Croaking  Pilling</p>	<p><b>RANCH</b>  2  100% Cotton  India  54" - 137 cm  1.75" (4.4 cm)  1.75" (4.4 cm)  No  10.2  S  N/A  15,000 DR Wyzenbeek Cotton Duck  N/A  N/A  N/A  N/A  N/A  N/A</p>
	<p><b>PATTERN</b>  Number of Cols.  Content  Country of Origin  Width  Vertical  Horizontal  Railroaded  Weight (oz/ln yd)  Care Code  Flammability  Surface Abrasion  Tear Strength  Seam Slippage  Breaking Strength  Colorfastness to Light  Croaking  Pilling</p>	<p><b>ROADHOUSE</b>  5  100% Cotton  India  54" - 137 cm  6.5" (16.5 cm)  6.625" (16.8 cm)  No  10.2  S  N/A  15,000 DR Wyzenbeek Cotton Duck  N/A  N/A  N/A  N/A  N/A  N/A</p>
	<p><b>PATTERN</b>  Number of Cols.  Content  Country of Origin  Width  Vertical  Horizontal  Railroaded  Weight (oz/ln yd)  Care Code  Flammability  Surface Abrasion  Tear Strength  Seam Slippage  Breaking Strength  Colorfastness to Light  Croaking  Pilling</p>	<p><b>SENSA</b>  19  100% Polyester  Belgium  55" - 140 cm  N/A  N/A  No  11.4  S (Dry Clean) – W ( Wash)  UFAC Class/e 1, Cal. 117  40,000 strokes/lissages Martindale  Warp: 4 lbf, Filling: 11 lbf  Warp: 122 lbf, Filling: 234 lbf  Warp: 50 lbf, Filling: 60 lbf  Class/e 4  Wet: Class/e 5, Dry: Class/e 5  Class/e 5</p>

	<p><b>PATTERN</b></p> <p>Number of Cols. 3  Content 100% Cotton  Country of Origin India  Width 54" - 137 cm  Vertical 1.75" (4.4 cm)  Horizontal 2.25" (5.7 cm)  Railroaded No  Weight (oz/lb yd) 10.2  Care Code S  Flammability N/A  Surface Abrasion 15,000 DR Wyzenbeek Cotton Duck  Tear Strength N/A  Seam Slippage N/A  Breaking Strength N/A  Colorfastness to Light N/A  Croaking N/A  Pilling N/A</p>	<p><b>SILVERADO</b></p> <p>3  100% Cotton  India  54" - 137 cm  1.75" (4.4 cm)  2.25" (5.7 cm)  No  10.2  S  N/A  15,000 DR Wyzenbeek Cotton Duck  N/A  N/A  N/A  N/A  N/A</p>
	<p><b>PATTERN</b></p> <p>Number of Cols. 12  Content 100% Cotton  Country of Origin India  Width 54" - 137 cm  Vertical 0.25" (0.64 cm)  Horizontal 0.25" (0.64 cm)  Railroaded No  Weight (oz/lb yd) 11.3  Care Code S  Flammability UFAC Class/e 1, Cal. 117  Surface Abrasion 9,000 DR Wyzenbeek Cotton Duck  Tear Strength Warp: resists tear, Filling: 25.2 lbf  Seam Slippage Warp: 91.2 lbf, Filling: 103.9 lbf  Breaking Strength Warp: 134.4 lbf, Filling: 95.7 lbf  Colorfastness to Light N/A  Croaking Wet: Class/e 4, Dry: Class/e 4.5  Pilling Class/e 4.5</p>	<p><b>STABLE</b></p> <p>12  100% Cotton  India  54" - 137 cm  0.25" (0.64 cm)  0.25" (0.64 cm)  No  11.3  S  UFAC Class/e 1, Cal. 117  9,000 DR Wyzenbeek Cotton Duck  Warp: resists tear, Filling: 25.2 lbf  Warp: 91.2 lbf, Filling: 103.9 lbf  Warp: 134.4 lbf, Filling: 95.7 lbf  N/A  Wet: Class/e 4, Dry: Class/e 4.5  Class/e 4.5</p>

	<p><b>PATTERN</b>  Number of Cols.  Content  Country of Origin  Width  Vertical  Horizontal  Railroaded  Weight (oz/lb yd)  Care Code  Flammability  Surface Abrasion  Tear Strength  Seam Slippage  Breaking Strength  Colorfastness to Light  Croaking  Pilling</p>	<p><b>TOTEM</b>  3  100% Cotton  India  54" - 137 cm  N/A  1" (2.5 cm)  No  10.2  S  N/A  15,000 DR Wyzenbeek Cotton Duck  N/A  N/A  N/A  N/A  N/A  N/A</p>
	<p><b>PATTERN</b>  Number of Cols.  Content  Country of Origin  Width  Vertical  Horizontal  Railroaded  Weight (oz/lb yd)  Care Code  Flammability  Surface Abrasion  Tear Strength  Seam Slippage  Breaking Strength  Colorfastness to Light  Croaking  Pilling</p>	<p><b>WOODBINE</b>  14  100% Cotton  India  54" - 137 cm  3.5" (8.9 cm)  3.75" (9.5 cm)  No  11.4  S  UFAC Class/e 1, Cal. 117  9,000 DR Wyzenbeek Cotton Duck  Warp: resists tear, Filling: 25.2 lbf  Warp: 91.2 lbf, Filling: 103.9 lbf  Warp: 134.4 lbf, Filling: 95.7 lbf  N/A  Wet: Class/e 4, Dry: Class/e 4.5  Class/e 4.5</p>