



JOANNE / J.F. FABRICS

PRODUCT INFORMATION

Elegant Attire - J3751/2/3/4

Elegant Attire

By Color

Dress your room in Elegant Attire!

This sophisticated collection offers the most magnificent designs in exquisite colorations to satisfy the most discerning of buyers. This four book By Color Series includes 18 designs for a total of 149 skus that offer endless possibilities. We believe Elegant Attire By Color is one of the best collections we have ever done. Elegant Attire is exclusive to Joanne Fabrics/J.F. Fabrics.






Elegant Attire

By Color

	<p>PATTERN Number of Cols. 3 Content 76% Cotton, 24% Rayon Country of Origin USA Width 54" - 137 cm Vertical 12.75" (32.4 cm) Horizontal 13.5" (34.3 cm) Railroaded No Weight (oz/lb yd) 21 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 92 lbf, Filling: 95.3 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>ALBION 3 76% Cotton, 24% Rayon USA 54" - 137 cm 12.75" (32.4 cm) 13.5" (34.3 cm) No 21 S (Dry Clean) Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 92 lbf, Filling: 95.3 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 2 Content 53% Polyester, 47% Rayon Country of Origin USA Width 54" - 137 cm Vertical 11.5" (29.2 cm) Horizontal 9" (22.9 cm) Railroaded No Weight (oz/lb yd) 20.5 Care Code S (Dry Clean) Flammability UFAC Class/e 1, NFPA 260 & Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 73.5 lbf, Filling: 64.3 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>ALDO 2 53% Polyester, 47% Rayon USA 54" - 137 cm 11.5" (29.2 cm) 9" (22.9 cm) No 20.5 S (Dry Clean) UFAC Class/e 1, NFPA 260 & Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 73.5 lbf, Filling: 64.3 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 4 Content 77% Rayon, 23% Polyester Country of Origin USA Width 54" - 137 cm Vertical 10.125" (25.7 cm) Horizontal 9" (22.9 cm) Railroaded Yes Weight (oz/lb yd) 17.8 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 24,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 71.9 lbf, Filling: 53.8 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>ALERO 4 77% Rayon, 23% Polyester USA 54" - 137 cm 10.125" (25.7 cm) 9" (22.9 cm) Yes 17.8 S (Dry Clean) Cal. 117 24,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 71.9 lbf, Filling: 53.8 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>

Elegant Attire

By Color

	<p>PATTERN Number of Cols. 5 Content 43% Rayon, 35% Polyester, 22% Cotton Country of Origin USA Width 54" - 137 cm Vertical 6.68" (17 cm) Horizontal 6.75" (17.1 cm) Railroaded No Weight (oz/ln yd) 21.8 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 95 lbf, Filling: 68.6 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>ARAMIS 5 43% Rayon, 35% Polyester, 22% Cotton USA 54" - 137 cm 6.68" (17 cm) 6.75" (17.1 cm) No 21.8 S (Dry Clean) Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 95 lbf, Filling: 68.6 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 3 Content 42% Cotton, 31% Polyester, 27% Rayon Country of Origin USA Width 54" - 137 cm Vertical 6.3" (16 cm) Horizontal 6.75" (17.1 cm) Railroaded Yes Weight (oz/ln yd) 24.8 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 53 lbf, Filling: 61.6 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>BALKIN 3 42% Cotton, 31% Polyester, 27% Rayon USA 54" - 137 cm 6.3" (16 cm) 6.75" (17.1 cm) Yes 24.8 S (Dry Clean) Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 53 lbf, Filling: 61.6 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 14 Content 59% Rayon, 41% Polyester Country of Origin USA Width 54" - 137 cm Vertical N/A Horizontal 0.313" (0.8 cm) Railroaded No Weight (oz/ln yd) 18.7 Care Code S (Dry Clean) Flammability UFAC Class/e 1, NFPA 260 & Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 97.1 lbf, Filling: 71.4 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>COSTA 14 59% Rayon, 41% Polyester USA 54" - 137 cm N/A 0.313" (0.8 cm) No 18.7 S (Dry Clean) UFAC Class/e 1, NFPA 260 & Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 97.1 lbf, Filling: 71.4 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>

Elegant Attire

By Color

	<p>PATTERN Number of Cols. 5 Content 58% Rayon, 42% Polyester Country of Origin USA Width 54" - 137 cm Vertical 4.2" (10.7 cm) Horizontal 6.75" (17.1 cm) Railroaded Yes Weight (oz/ln yd) 18.1 Care Code S (Dry Clean) Flammability UFAC Class/e 1, NFPA 260 & Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 95.1 lbf, Filling: 66.2 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>DELANO 5 58% Rayon, 42% Polyester USA 54" - 137 cm 4.2" (10.7 cm) 6.75" (17.1 cm) Yes 18.1 S (Dry Clean) UFAC Class/e 1, NFPA 260 & Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 95.1 lbf, Filling: 66.2 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 6 Content 54% Rayon, 46% Polyester Country of Origin USA Width 54" - 137 cm Vertical 1.125" (2.8 cm) Horizontal 1.125" (2.8 cm) Railroaded No Weight (oz/ln yd) 16.8 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 83.8 lbf, Filling: 56.1 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>FRANCO 6 54% Rayon, 46% Polyester USA 54" - 137 cm 1.125" (2.8 cm) 1.125" (2.8 cm) No 16.8 S (Dry Clean) Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 83.8 lbf, Filling: 56.1 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 12 Content 37% Polyester, 35% Cotton, 28% Rayon Country of Origin USA Width 54" - 137 cm Vertical 0.375" (0.9 cm) Horizontal 0.375" (0.9 cm) Railroaded No Weight (oz/ln yd) 21.3 Care Code S (Dry Clean) Flammability UFAC Class/e 1, NFPA 260, Cal. 117 & MVSS302 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 113.3 lbf, Filling: 75.16 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>HARVEY 12 37% Polyester, 35% Cotton, 28% Rayon USA 54" - 137 cm 0.375" (0.9 cm) 0.375" (0.9 cm) No 21.3 S (Dry Clean) UFAC Class/e 1, NFPA 260, Cal. 117 & MVSS302 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 113.3 lbf, Filling: 75.16 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>



Elegant Attire

By Color

	<p>PATTERN Number of Cols. 14 Content 75% Rayon, 25% Polyester Country of Origin USA Width 54" - 137 cm Vertical 27.375" (69.5 cm) Horizontal 27" (69 cm) Railroaded No Weight (oz/ln yd) 30.4 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 24,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 95 lbf, Filling: 83 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>MADERA 14 75% Rayon, 25% Polyester USA 54" - 137 cm 27.375" (69.5 cm) 27" (69 cm) No 30.4 S (Dry Clean) Cal. 117 24,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 95 lbf, Filling: 83 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 14 Content 57% Rayon, 43% Polyester Country of Origin USA Width 54" - 137 cm Vertical 0.313" (0.8 cm) Horizontal 0.313" (0.8 cm) Railroaded No Weight (oz/ln yd) 17.9 Care Code S (Dry Clean) Flammability Ufac Classe/ 1, NFPA 260 & Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 73.4 lbf, Filling: 42.5 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>MASON 14 57% Rayon, 43% Polyester USA 54" - 137 cm 0.313" (0.8 cm) 0.313" (0.8 cm) No 17.9 S (Dry Clean) Ufac Classe/ 1, NFPA 260 & Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 73.4 lbf, Filling: 42.5 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 8 Content 61% Rayon, 39% Polyester Country of Origin USA Width 54" - 137 cm Vertical 2" (5 cm) Horizontal 2.25" (5.7 cm) Railroaded No Weight (oz/ln yd) 19.7 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 75.5 lbf, Filling: 48 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>NIRA 8 61% Rayon, 39% Polyester USA 54" - 137 cm 2" (5 cm) 2.25" (5.7 cm) No 19.7 S (Dry Clean) Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 75.5 lbf, Filling: 48 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>



Elegant Attire

By Color

	<p>PATTERN Number of Cols. 7 Content 60% Rayon, 40% Polyester Country of Origin USA Width 54" - 137 cm Vertical 4.375" (11.1 cm) Horizontal 4.5" (11.4 cm) Railroaded Yes Weight (oz/ln yd) 19 Care Code S (Dry Clean) Flammability UFAC Classe/ 1, NFPA 260 & Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 96.5 lbf, Filling: 81.1 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>OSLO 7 60% Rayon, 40% Polyester USA 54" - 137 cm 4.375" (11.1 cm) 4.5" (11.4 cm) Yes 19 S (Dry Clean) UFAC Classe/ 1, NFPA 260 & Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 96.5 lbf, Filling: 81.1 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 14 Content 44% Polyester, 39% Cotton, 17% Rayon Country of Origin USA Width 54" - 137 cm Vertical 2.3" (5.9 cm) Horizontal 2.25" (5.7 cm) Railroaded No Weight (oz/ln yd) 17.3 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 50 lbf, Filling: 38 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>PAIGE 14 44% Polyester, 39% Cotton, 17% Rayon USA 54" - 137 cm 2.3" (5.9 cm) 2.25" (5.7 cm) No 17.3 S (Dry Clean) Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 50 lbf, Filling: 38 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 17 Content 59% Rayon, 41% Polyester Country of Origin USA Width 54" - 137 cm Vertical 0.875" (2.2 cm) Horizontal 0.6" (1.5 cm) Railroaded No Weight (oz/ln yd) 18.7 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 102.3 lbf, Filling: 77.9 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>REDFORD 17 59% Rayon, 41% Polyester USA 54" - 137 cm 0.875" (2.2 cm) 0.6" (1.5 cm) No 18.7 S (Dry Clean) Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 102.3 lbf, Filling: 77.9 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>

Elegant Attire

By Color

	<p>PATTERN Number of Cols. 9 Content 63% Rayon, 37% Polyester Country of Origin USA Width 54" - 137 cm Vertical 3.375" (8.6 cm) Horizontal N/A Railroaded Yes Weight (oz/lb yd) 20.8 Care Code S (Dry Clean) Flammability Cal. 117 Surface Abrasion 24,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 85 lbf, Filling: 60 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>RUBEN 9 63% Rayon, 37% Polyester USA 54" - 137 cm 3.375" (8.6 cm) N/A Yes 20.8 S (Dry Clean) Cal. 117 24,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 85 lbf, Filling: 60 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 4 Content 64% Rayon, 36% Polyester Country of Origin USA Width 54" - 137 cm Vertical N/A Horizontal N/A Railroaded No Weight (oz/lb yd) 11.5 Care Code S (Dry Clean) Flammability UFAC Classe/ 1, Cal. 117 Surface Abrasion 30,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 40 lbf, Filling: 37.6 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>WALSH 4 64% Rayon, 36% Polyester USA 54" - 137 cm N/A N/A No 11.5 S (Dry Clean) UFAC Classe/ 1, Cal. 117 30,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 40 lbf, Filling: 37.6 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>
	<p>PATTERN Number of Cols. 8 Content 50% Cotton, 50% Rayon Country of Origin USA Width 54" - 137 cm Vertical 11.875" (30.2 cm) Horizontal 13.5" (34.3 cm) Railroaded No Weight (oz/lb yd) 18.9 Care Code S (Dry Clean) Flammability UFAC Classe/ 1, NFPA 260 & Cal. 117 Surface Abrasion 24,000 DR Wyzenbeek Cotton Duck Tear Strength Warp: 6 lbf, Filling: 6 lbf Tensile Strength Warp: 50 lbf, Filling: 50 lbf Seam Slippage Warp: 50 lbf, Filling: 35.5 lbf Colorfastness to Light Class/e 3 (40 hours) Crocking Wet: Class/e 3 - Dry: Class/e 4 Pilling Class/e 3</p>	<p>WILFRED 8 50% Cotton, 50% Rayon USA 54" - 137 cm 11.875" (30.2 cm) 13.5" (34.3 cm) No 18.9 S (Dry Clean) UFAC Classe/ 1, NFPA 260 & Cal. 117 24,000 DR Wyzenbeek Cotton Duck Warp: 6 lbf, Filling: 6 lbf Warp: 50 lbf, Filling: 50 lbf Warp: 50 lbf, Filling: 35.5 lbf Class/e 3 (40 hours) Wet: Class/e 3 - Dry: Class/e 4 Class/e 3</p>