



JOANNE / J.F. FABRICS

PRODUCT INFORMATION

Raffiki - J3761

RAFFIKI

Texture, Texture, Texture! This collection of Faux woven raffia will inspire you to decorate indoors and out - dress up that patio area, create a new outdoor room with raffia screens, woven seating or even place mats. Give your kitchen or family room a tropical feel with these fun designs Bongo, Cargo, and Tiki. These fabrics are woven with a 100% Polypropylene fiber and can withstand up to 500 hours of direct sunlight. This remarkable product is available in 17 nature inspired skus.



RAFFIKI

	<p>PATTERN Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Seam Slippage Tensile Strength (Prior to UV Exposure) Tensile Strength (500 hrs Exposure to UV light) Colorfastness to Light</p>	<p>BONGO 5 100% Polypropylene South Korea 58" - 147 cm N/A N/A No 19.7 N/A W - Hand Wash N/A 15,000 DR Wyzenbeek Wire Screen Warp: 37 lbf, Filling: 44.55 lbf Warp: 461 lbf, Filling: 396 lbf Warp: 130 lbf, Filling: 87 lbf 500 hours</p>
	<p>PATTERN Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Seam Slippage Tensile Strength (Prior to UV Exposure) Tensile Strength (500 hrs Exposure to UV light) Colorfastness to Light</p>	<p>CARGO 6 100% Polypropylene South Korea 58" - 147 cm N/A N/A No 19.7 N/A W - Hand Wash N/A 15,000 DR Wyzenbeek Wire Screen Warp: 37 lbf, Filling: 44.55 lbf Warp: 461 lbf, Filling: 396 lbf Warp: 130 lbf, Filling: 87 lbf 500 hours</p>
	<p>PATTERN Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Seam Slippage Tensile Strength (Prior to UV Exposure) Tensile Strength (500 hrs Exposure to UV light) Colorfastness to Light</p>	<p>TIKI 6 100% Polypropylene South Korea 58" - 147 cm N/A N/A No 19.7 N/A W - Hand Wash N/A 15,000 DR Wyzenbeek Wire Screen Warp: 37 lbf, Filling: 44.55 lbf Warp: 461 lbf, Filling: 396 lbf Warp: 130 lbf, Filling: 87 lbf 500 hours</p>