

JOANNE / J.F. FABRICS


PRODUCT INFORMATION

The Tannery III - J3771

THE TANNERY III

Introducing our third remarkable faux leather collection. The Tannery III offers nine new designs in the most intriguing textures. All designs are sampled in traditional natural leather colors and a few select designs in highly decorative off-white, pink, lime, and baby blue.

These fabrics are constructed primarily of PVC (poly vinyl chloride) with polyester and cotton backing to add to their stability. These goods have a supple hand, distressed finishes and are very easy to care for. The Tannery III has a total of 51 skus and is exclusive to Joanne/J.F. Fabrics.



THE TANNERY III



PATTERN

Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Tear Strength Crockina Colorfastness to Light

COBRA


84% PVC, 16% Polyester Germany 59" - 150 cm 25.6" (65 cm) 11.8" (30 cm) No 28.3

W - Hand Wash UFAC Class/e 1, Cal. 117 & MVSS 302 40,000 strokes Martindale

Warp: 12 lbf, Filling: 12 lbf Wet: Class/e 5, Dry: Class/e 5

Class/e 3

N/A



PATTERN

Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/In yd) Finish Care Code Flammability Surface Abrasion Tear Strength Crocking Colorfastness to Light


CROC

77% PVC, 23% Cotton Germany 59" - 150 cm 14.25" (36 cm) 13.75" (35 cm) No 31.2 N/A

W - Hand Wash UFAC Class/e 1, Cal. 117 & MVSS 302 40,000 strokes Martindale

Warp: 12 lbf, Filling: 12 lbf Wet: Class/e 5, Dry: Class/e 5

Class/e 5



PATTERN

Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Tear Strength Crocking Colorfastness to Light

GRASSY 84% PVC, 16% Polyester Germany 59" - 150 cm N/A N/A No 28.3 N/A

W - Hand Wash UFAC Class/e 1, Cal. 117 & MVSS 302

40.000 strokes Martindale Warp: 12 lbf, Filling: 12 lbf Wet: Class/e 5, Dry: Class/e 5

Class/e 3

THE TANNERY III



PATTERN

Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Tear Strength Crockina Colorfastness to Light

HUT

85% PVC, 15% Polyester

Germany 59" - 150 cm

N/A N/A

No 28.3 N/A

W - Hand Wash

UFAC Class/e 1, Cal. 117 & MVSS 302

40,000 strokes Martindale Warp: 12 lbf, Filling: 12 lbf Wet: Class/e 5, Dry: Class/e 5

Class/e 3



PATTERN Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/In yd) Finish Care Code Flammability Surface Abrasion Tear Strength Crocking Colorfastness to Light

MAMMOTH

77% PVC, 23% Cotton

Germany 59" - 150 cm

N/A N/A No 31.2 N/A

W - Hand Wash

UFAC Class/e 1, Cal. 117 & MVSS 302

40,000 strokes Martindale Warp: 12 lbf, Filling: 12 lbf Wet: Class/e 5, Dry: Class/e 5

Class/e 5



PATTERN

Number of Cols. Content

Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Tear Strength Crocking Colorfastness to Light

PANTHER

63% PVC, 18% Polyester, 17% Cotton,

2% Polyurethane

57" - 145 cm

N/A N/A No 28.3 N/A

W - Hand Wash

UFAC Class/e 1, Cal. 117 & MVSS 302

40,000 strokes Martindale Warp: 12 lbf, Filling: 12 lbf Wet: Class/e 5, Dry: Class/e 5

Class/e 3

THE TANNERY III



PATTERN

Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Tear Strength Crockina Colorfastness to Light

RAWHIDE

80% PVC, 20% Polyester Germany 59" - 150 cm

N/A N/A No 30.1 N/A

W - Hand Wash

UFAC Class/e 1, Cal. 117 & MVSS 302

40,000 strokes Martindale Warp: 12 lbf, Filling: 12 lbf Wet: Class/e 5, Dry: Class/e 5

Class/e 4



PATTERN Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Tear Strength Crocking

Colorfastness to Light

REPTILE

77% PVC, 23% Cotton

Germany 59" - 150 cm

N/A N/A No 31.2 N/A

W - Hand Wash

UFAC Class/e 1, Cal. 117 & MVSS 302

40,000 strokes Martindale Warp: 12 lbf, Filling: 12 lbf Wet: Class/e 5, Dry: Class/e 5

Class/e 5



PATTERN Number of Cols. Content Country of Origin Width Vertical Horizontal Railroaded Weight (oz/ln yd) Finish Care Code Flammability Surface Abrasion Tear Strength Crocking Colorfastness to Light

TURTLE

77% PVC, 23% Cotton Germany 59" - 150 cm 24.75" (63 cm) 29.5" (75 cm) No 31.2

N/A W - Hand Wash

UFAC Class/e 1, Cal. 117 & MVSS 302

40.000 strokes Martindale Warp: 12 lbf, Filling: 12 lbf Wet: Class/e 5, Dry: Class/e 5

Class/e 5